

Claims:

1. A method in the manufacture of coating, in which method the coating is manufactured by mixing together two or more components, **characterised in that**
5 the mixing of components is carried out by mixing two or more components in two or more mixing zones arranged in series and/or in parallel, of which at least some are pressurised at the pressure level about 100-1000 kPa.
2. A method according to Claim 1, **characterised in that** the pressure level in a
10 mixing zone is preferably about 200-500 kPa.
3. A method according to Claim 1 or 2, **characterised in that** the components to be mixed are in a pressurised space also at least between the pressurised mixing zones.
- 15 4. A method according to Claim 3, **characterised in that** in the method a mixing arrangement is used, which is pressurised from the component feeding pumps to the machine container.
- 20 5. A method according to any of the above mentioned Claims, **characterised in that** at least one of the components to be mixed is led to the mixing zone through a deaeration means.
- 25 6. A method according to any of the above mentioned Claims, **characterised in that** the temperature of the coating is controlled with a temperature control system arranged in connection with one or more mixing zones.
7. A method according to any of the above mentioned Claims, **characterised in that** the components mixed in one or more mixing zones are fed to a pressure screen.

8. A method according to any of the above mentioned Claims, **characterised in that** the components mixed in one or more mixing zones are fed to a separator, into which an underpressure of approximately 0.5-50 kPa and preferably approximately 2-15 kPa is arranged.

5

9. A method according to Claim 8, **characterised in that** from the separator the mixture is transferred for screening and from the screening it is further transferred to the coating station.

10

10. A method according to any of the above mentioned Claims, **characterised in that** the properties of the mixture and/or a part of the mixture formed by the mixed components are measured with one or more measurement devices arranged after at least one mixing zone.

15

11. An arrangement in the manufacture of coating, which comprises at least means for transferring and mixing the coating components, **characterised in that** the means for mixing the components are arranged to two or more serial and/or parallel mixing zones, of which at least some are pressurised to a pressure level approximately 100-1000 kPa.

20

12. An arrangement according to Claim 11, **characterised in that** into the mixing zone a pressure level has been arranged, which preferably approximately 200-500 kPa.

25

13. An arrangement according to Claim 11 or 12, **characterised in that** the arrangement is also pressurised between the mixing zones.

30

14. An arrangement according to any of Claims 11-13 **characterized in that** there are means comprised for removing and/or reducing air from one or more components being fed to a mixing zone.